



Georgia-Pacific
Chemicals

GP[®] BKR-2620 Coating Resin

PRODUCT INFORMATION

INTRODUCTION

GP[®] BKR-2620 coating resin is a solid, heat-reactive, modified phenolic resin. It can be used with a wide selection of solvents and is compatible with plasticizers and polyvinyl butyral resins. Films made with unplasticized GP BKR-2620 resin have greater flexibility than those made with other unmodified phenolic resin baking solutions.

APPLICATIONS

GP BKR-2620 resin is used in nitrile adhesives; can, pail and drum linings; pipe coatings; and as a metal primer.

CERTIFICATIONS

GP BKR-2620 coating resin is compliant with FDA 21 CFR Part 175 Indirect Food Additives: Adhesives and Components of Coatings per 175.105 as a component of an adhesive and 175.300 as a resinous and polymeric coating. It complies with 176.170 Indirect Food Additives: Paper and Paperboard Components in contact with aqueous and fatty foods as a component of adhesives and resinous and polymeric coatings. It also complies with 176.180 Indirect Food Additives: Paper and Paperboard Components in contact with dry foods as a component of adhesives and resinous and polymeric coatings and 177.1210 as a component in closures with sealing gaskets for food containers.

STORAGE AND HANDLING

It is recommended that heat-reactive GP BKR-2620 resin be stored in a dry place at temperatures at or below 50 °F (10 °C) to optimize shelf life. Storage in sunlight should be avoided. Storage life is dependent on your product's formulation using GP BKR-2620 resin. This product should be stored and used in areas with good ventilation.

The proper personal protective equipment should be worn whenever GP BKR-2620 resin is used or handled. For safety and health information, please refer to the Safety Data Sheet available from Georgia-Pacific Chemicals.

TYPICAL PROPERTIES

Form	Lump Solid
Color, Gardner (50:50 in toluene)	12 max.
Softening Point, °F (°C)	180 – 210 (82 – 99)

Limits listed are targeted specifications.

866-4GP-CHEM

GPChemical@gapac.com
www.gp-chemicals.com