



Georgia-Pacific
Chemicals

GP[®] BKUA-2353 Resin Dispersion

PRODUCT INFORMATION

INTRODUCTION

GP[®] BKUA-2353 is a non-heat-reactive aqueous dispersion for waterborne adhesives, sealants and coatings systems. It provides improved adhesion and green strength development in acrylic latex adhesives. GP BKUA-2353 is stabilized with a non-ionic emulsifier as well as a coupling solvent additive.

APPLICATIONS

GP BKUA-2353 dispersion is used in acrylic latex adhesives in applications such as automotive brakes.

STORAGE AND HANDLING

The dispersion is freeze-thaw, shear and storage stable. Extended storage at high temperatures should be avoided to prolong the useful life of the resins. It is suggested that the resin be stored in a cool, dry location at temperatures between 45°F (7°C) and 60°F (16°C). Storage below 45°F is not recommended in order to prevent freezing. This product should be stored and used in areas with good ventilation.

The proper personal protective equipment should be worn whenever GP BKUA-2353 dispersion is used or handled. For safety and health information, please refer to the Safety Data Sheet for GP BKUA-2353 dispersion available from Georgia-Pacific Chemicals.

TYPICAL PROPERTIES

Appearance	Milky white liquid
Viscosity @ 25°C, cP (mPa*sec)	2000 - 5000
Solids, wt. %	43 - 47
Specific Gravity @ 25°C	Approximately 1.06 – 1.07
Co-Solvents	Propylene glycol MPE and isopropanol

866-4GP-CHEM

GPChemical@gapac.com
www.gp-chemicals.com