

# GP<sup>®</sup> CK-2103 Coating Resin

## PRODUCT INFORMATION

### INTRODUCTION

GP<sup>®</sup> CK-2103 resin is a novolac resin modifier for alkyd and epoxy air dry coatings designed to improve water resistance, hardness, gloss and adhesion. Coatings made with GP CK-2103 resin dry faster than those made with GP CK-2432 resin and will darken on drying.

### APPLICATIONS

Used primarily in air-dried and cooked protective coatings for marine, maintenance and other metal protection applications, GP CK-2103 resin can be used in other coating applications and in ink formulations.

### CERTIFICATIONS

GP CK-2103 coating resin is compliant with the U.S. Food and Drug Administration (FDA) according to Title 21 CFR §175.105, §175.300, §176.180, §177.1210 and, §176.170 as resinous and polymeric coatings.

### STORAGE AND HANDLING

GP CK-2103 resin is non heat-reactive and shipped in bags. It should be stored in a dry location at temperatures at or below 25°C (77°F). Storage in sunlight should be avoided. Resin storage life under the recommended conditions is two years, possibly longer dependent on your product's formulation using GP CK-2103 resin. This product should be stored and used in areas with good ventilation.

The proper personal protective equipment should be worn whenever GP CK-2103 resin is used or handled. For safety and health information, please refer to the Safety Data Sheet for GP CK-2103 resin available from Georgia-Pacific Chemicals.

### TYPICAL PROPERTIES

Appearance	Solid, flake
Softening Point, °F (°C)	215 – 245 (102 – 118)
Gardener (50:50 in xylene)	5 maximum
Specific Gravity @ 25°C	Approximately 1.06 – 1.08

**866-4GP-CHEM**

GPChemical@gapac.com  
www.gp-chemicals.com