



Georgia-Pacific
Chemicals

GP[®] CK-2500 Coating Resin

PRODUCT INFORMATION

INTRODUCTION

GP[®] CK-2500 coating resin is a novolac resin modifier for alkyd and epoxy air dry coatings designed to improve water resistance, hardness, gloss and intercoat adhesion. GP CK-2500 resin enables higher solids and lower viscosity solutions than those made with GP CK-2400 resin.

APPLICATIONS

Used primarily in low VOC applications and cold blend and cooked (reacted) coatings for marine, maintenance and other metal protection applications, GP CK-2500 resin can also be used in other coating applications and in ink formulations.

STORAGE AND HANDLING

GP CK-2500 resin is non heat-reactive and shipped in bags. It should be stored in a dry, well-ventilated location at temperatures at or below 25 °C (77 °F). Storage in sunlight should be avoided. Resin storage life under the recommended conditions is two years, possibly longer dependent on your product's formulation using GP CK-2500 resin. This product should be stored and used in areas with good ventilation.

The proper personal protective equipment should be worn whenever GP CK-2500 resin is used or handled. For safety and health information, please refer to the Safety Data Sheet for GP CK-2500 resin available from Georgia-Pacific Chemicals.

TYPICAL PROPERTIES

Appearance	Solid, flake
Softening Point, °F (°C)	220 – 240 (104 – 116)
Gardener (50:50 in xylene)	8 maximum
Specific Gravity @ 25°C	Approximately 1.07 – 1.10

866-4GP-CHEM

GPChemical@gapac.com
www.gp-chemicals.com