



**Georgia-Pacific**  
Chemicals

# GP<sup>®</sup> BKS-2605 Coating Resin

## PRODUCT INFORMATION

### INTRODUCTION

GP<sup>®</sup> BKS-2605 heat-reactive phenolic resin solution in ethanol and n-butanol is formulated to provide chemical resistance for protective coatings for rigid metallic substrates.

### APPLICATIONS

GP BKS-2605 resin is used primarily in applications such as drums and pails, pipes, tanks and railcars.

### CERTIFICATIONS

GP BKS-2605 coating resin is compliant with FDA 21 CFR Part 175 Indirect Food Additives: Adhesives and Components of Coatings per 175.105 as a component of an adhesive and 175.300 as a resinous and polymeric coating. It also complies with 177.1210 as a component in closures with sealing gaskets for food containers.

### STORAGE AND HANDLING

It is recommended that heat-reactive GP BKS-2605 resin be stored in a dry place at temperatures at or below 50°F (10°C) to optimize shelf life. Storage in sunlight should be avoided. Storage life is dependent on your product's formulation using GP BKS-2605 resin. This product should be stored and used in areas with good ventilation.

The proper personal protective equipment should be worn whenever GP BKS-2605 resin is used or handled. For safety and health information, please refer to the Safety Data Sheet available from Georgia-Pacific Chemicals.

### TYPICAL PROPERTIES

Form	Solution in ethanol and n-butanol
Viscosity @ 25°C, cP (mPa*sec)	750 – 1,500
Solids, wt. %	62 – 66
Specific Gravity @ 25°C	1.08 – 1.12

**866-4GP-CHEM**

GPChemical@gapac.com  
www.gp-chemicals.com