



Georgia-Pacific
Chemicals

GP[®] BKS-2600 Coating Resin

PRODUCT INFORMATION

INTRODUCTION

GP[®] BKS-2600 heat-reactive phenolic resin solution in ethanol is formulated to provide chemical resistance for protective coatings for rigid metallic substrates.

APPLICATIONS

GP BKS-2600 resin is used primarily in applications such as drums and pails, pipes, tanks and railcars.

CERTIFICATIONS

GP BKS-2600 coating resin is compliant with FDA 21 CFR Part 175 Indirect Food Additives: Adhesives and Components of Coatings per 175.105 as a component of an adhesive and 175.300 as a resinous and polymeric coating. It complies with 176.170 Indirect Food Additives: Paper and Paperboard Components in contact with aqueous and fatty foods as a component of adhesives and resinous and polymeric coatings. It also complies with 176.180 Indirect Food Additives: Paper and Paperboard Components in contact with dry foods as a component of adhesives and resinous and polymeric coatings and 177.1210 as a component in closures with sealing gaskets for food containers.

STORAGE AND HANDLING

It is recommended that heat-reactive GP BKS-2600 resin be stored in a dry place at temperatures at or below 50°F (10°C) to optimize shelf life. Storage in sunlight should be avoided. Storage life is dependent on your product's formulation using GP BKS-2600 resin. This product should be stored and used in areas with good ventilation.

The proper personal protective equipment should be worn whenever GP BKS-2600 resin is used or handled. For safety and health information, please refer to the Safety Data Sheet available from Georgia-Pacific Chemicals.

TYPICAL PROPERTIES

Form	Solution in ethanol
Viscosity @ 25°C, cP (mPa*sec)	700 – 1000
Solids, wt. %	52 – 56
Specific Gravity @ 25°C	Approximately 1.04 – 1.07

866-4GP-CHEM

GPChemical@gapac.com
www.gp-chemicals.com